



NATA Accredited Laboratory

Accreditation No: 15305

Accredited for compliance with
ISO/IEC 17025 - Testing

Laminex[®]

a division of Laminex Group Pty Ltd ABN 98 004 093 092

The Laminex Group Technology Centre

Postal Address: PO BOX 720, Wendouree, Vic 3355

Address: 22 Trewin St, Wendouree, Vic 3355

Telephone: (03) 5337 3613

Fax: (03) 5337 3647

**Test Report No.
20MDF-Lamiwood**

Date of Issue

17/08/2020

Client:

Laminex Australia

22 Trewin St

Wendouree

VIC 3355

This test report shall not be reproduced, except in full,
without written approval from The Laminex Group Technology Centre

The material contained in this report is confidential to the entity identified as 'Client' above.

As the sample(s) have been provided by the client, the results contained in this report apply only to the sample(s) as received.

Test Report No. 20MDF-Lamiwood

Date of Issue: 17/08/2020

Laminex Sample Reference No.	26214
Client Sample Reference No.	797255
Product:	16mm Laminex Lamiwood Moisture Resistant E0 MDF
Surface Treatment	Laminated both sides with decorative Low Pressure Melamine
Receive Date:	29/06/2020
Condition:	Good.
Testing Performed Date(s):	3-7/7/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>12 to 22mm MR E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.37	0.01	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-Lamiwood

Date of Issue: 17/08/2020

Laminex Sample Reference No.	25625
Client Sample Reference No.	775853
Product:	18mm Laminex Lamiwood Moisture Resistant E0 MDF
Surface Treatment	Laminated both sides with decorative Low Pressure Melamine
Receive Date:	10/03/2020
Condition:	Good.
Testing Performed Date(s):	17-19/3/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>12 to 22mm MR E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.42	0.01	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-Lamiwood

Date of Issue: 17/08/2020

Laminex Sample Reference No.	22575
Client Sample Reference No.	628208
Product:	25mm Laminex Lamiwood Moisture Resistant E0 MDF
Surface Treatment	Laminated both sides with decorative Low Pressure Melamine
Receive Date:	30/04/2018
Condition:	Good.
Testing Performed Date(s):	11-15/5/2018
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>22 to 33mm MR E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.36	0.02	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-Lamiwood

Date of Issue: 17/08/2020

Laminex Sample Reference No.	22928
Client Sample Reference No.	GymDec 423
Product:	32mm Laminex Lamiwood Moisture Resistant E0 MDF
Surface Treatment	Laminated both sides with decorative Low Pressure Melamine
Receive Date:	20/07/2018
Condition:	Good.
Testing Performed Date(s):	27-31/7/2018
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>22 to 33mm MR E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.32	0.00	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-Lamiwood

Date of Issue: 17/08/2020

Laminex Sample Reference No.	23488
Client Sample Reference No.	676358
Product:	18mm Laminex Decorwood Standard E0 MDF
Surface Treatment	Laminated both sides with decorative Low Pressure Melamine
Receive Date:	19/11/2018
Condition:	Good.
Testing Performed Date(s):	26-28/11/2018
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>12 to 22mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.36	0.01	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-Lamiwood

Date of Issue: 17/08/2020

Laminex Sample Reference No.	24089
Client Sample Reference No.	704282
Product:	25mm Laminex Decorwood Standard E0 MDF
Surface Treatment	Laminated both sides with decorative Low Pressure Melamine
Receive Date:	1/04/2019
Condition:	Good.
Testing Performed Date(s):	5-9/4/2019
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>22 to 33mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.45	0.02	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...

