



NATA Accredited Laboratory

Accreditation No: 15305

Accredited for compliance with
ISO/IEC 17025 - Testing

Laminex[®]

a division of Laminex Group Pty Ltd ABN 98 004 093 092

The Laminex Group Technology Centre

Postal Address: PO BOX 720, Wendouree, Vic 3355

Address: 22 Trewin St, Wendouree, Vic 3355

Telephone: (03) 5337 3613

Fax: (03) 5337 3647

**Test Report No.
20MDF-STD-E0**

Date of Issue

13/08/2020

**Client:
Laminex Australia
Tin Can Bay Rd
Gympie
QLD 4570**

This test report shall not be reproduced, except in full,
without written approval from The Laminex Group Technology Centre

The material contained in this report is confidential to the entity identified as 'Client' above.

As the sample(s) have been provided by the client, the results contained in this report apply only to the sample(s) as received.

Test Report No. 20MDF-STD-E0

Date of Issue: 13/08/2020

Laminex Sample Reference No.	26197
Client Sample Reference No.	CARB 9311
Product:	3mm Standard E0 MDF
Product Description: (Supplied by client)	50003034N
Surface Treatment	None (Raw)
Receive Date:	22/06/2020
Condition:	Good.
Testing Performed Date(s):	15-17/7/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	≤5mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.32	0.00	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-STD-E0

Date of Issue: 13/08/2020

Laminex Sample Reference No.	26166
Client Sample Reference No.	CARB 9290
Product:	6mm Standard E0 MDF
Product Description: (Supplied by client)	50006040CE
Surface Treatment	None (Raw)
Receive Date:	17/06/2020
Condition:	Good.
Testing Performed Date(s):	7-9/7/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>5 to 8mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.41	0.00	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-STD-E0

Date of Issue: 13/08/2020

Laminex Sample Reference No.	26192
Client Sample Reference No.	CARB 9306
Product:	9mm Standard E0 MDF
Product Description: (Supplied by client)	50009040N
Surface Treatment	None (Raw)
Receive Date:	22/06/2020
Condition:	Good.
Testing Performed Date(s):	14-16/7/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>8 to 12mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.39	0.00	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-STD-E0

Date of Issue: 13/08/2020

Laminex Sample Reference No.	26180
Client Sample Reference No.	CARB 9304
Product:	12mm Standard E0 MDF
Product Description: (Supplied by client)	50012040N
Surface Treatment	None (Raw)
Receive Date:	17/06/2020
Condition:	Good.
Testing Performed Date(s):	10-14/7/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>8 to 12mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.27	0.00	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-STD-E0

Date of Issue: 13/08/2020

Laminex Sample Reference No.	26194
Client Sample Reference No.	CARB 9308
Product:	16mm Standard E0 MDF
Product Description: (Supplied by client)	50016053N
Surface Treatment	None (Raw)
Receive Date:	22/06/2020
Condition:	Good.
Testing Performed Date(s):	14-16/7/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>12 to 22mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.38	0.00	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-STD-E0

Date of Issue: 13/08/2020

Laminex Sample Reference No.	26244
Client Sample Reference No.	CARB 9338
Product:	18mm Standard E0 MDF
Product Description: (Supplied by client)	50018034CN
Surface Treatment	None (Raw)
Receive Date:	8/07/2020
Condition:	Good.
Testing Performed Date(s):	31/7/2020 - 4/8/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>12 to 22mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.29	0.00	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-STD-E0

Date of Issue: 13/08/2020

Laminex Sample Reference No.	26274
Client Sample Reference No.	CARB 9341
Product:	25mm Standard E0 MDF
Product Description: (Supplied by client)	50025034N
Surface Treatment	None (Raw)
Receive Date:	15/07/2020
Condition:	Good.
Testing Performed Date(s):	5-7/8/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>22 to 33mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.42	0.00	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...



Test Report No. 20MDF-STD-E0

Date of Issue: 13/08/2020

Laminex Sample Reference No.	26221
Client Sample Reference No.	CARB 9322
Product:	32mm Standard E0 MDF
Product Description: (Supplied by client)	50032034N
Surface Treatment	None (Raw)
Receive Date:	1/07/2020
Condition:	Good.
Testing Performed Date(s):	22-24/7/2020
Specification Standard	AS/NZS 1859.2:2017
Product Classification	>22 to 33mm STD E0 MDF

Test	Method	Unit	Result		Product limit		Compliance
			Mean	Std Dev	Limit Value	Standard Clause	
Formaldehyde Emission	AS/NZS 4266.1: 2017 Section 17	mg/L	0.38	0.02	Maximum 0.5 (E0)	Clause 6.3 Table 1	PASS E0

Formaldehyde Emission Class: E0

Comments
As agreed to by the client, compliance to product limits is based solely on the reported test result(s) and no uncertainty of measurement shall be taken into account.

Approved Signatory:

Laboratory Manager (J. Smolenaers)...

